



DRAFT TANZANIA STANDARD

Standard Classification for Sizes of Aggregate for Road and Bridge Construction

DRAFT STANDARD

TANZANIA BUREAU OF STANDARDS

0 National Foreword

The Tanzania Bureau of standards is the statutory national standards body for Tanzania, established under the act.No.3 of 1975, amended by act.No.2 of 2009.

This draft Tanzania Standard is being prepared by BCDC 5 Roads Technical Committee under the supervision of the Building and Construction Divisional Standards committee (BCDC).

In the preparation of this draft Tanzania Standard assistance was derived from ***ASTM D448-12 (reapproved 2022) Standard Classification for Sizes of Aggregate for Road and Bridge Construction. published by American Society for Testing and Materials (ASTM)***

DRAFT STANDARD

1 Scope

This classification defines aggregate size number designations and standard size ranges for mechanical sieve analyses of coarse aggregate and screenings for use in the construction and maintenance of various types of highways and bridges.

The standard does not specify production tolerances or quality control requirements, which shall be defined in relevant material specifications.

2 Normative references

The following referenced documents are indispensable for application of this standard. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ASTM Standards:

C136/C136M Test Method for Sieve Analysis of Fine and Coarse Aggregates

D8 Terminology Relating to Materials for Roads and Pavements

D75/D75M Practice for Sampling Aggregates

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

3 Terminology

For definitions of terms used in this standard, see Terminology D8.

4 Significance and Use

Some contract documents specify certain aggregate sizes for specific uses or may suggest one or more of these sizes as appropriate for the preparation of various end-product mixtures. In some cases, closer limits on variability of the aggregate grading are required.

5 Manufacture

The standard sizes of aggregate described in this classification are manufactured by means of any suitable process used to separate raw material into the desired size ranges.

Production of standard sizes by blending two or more different components is permitted.

6 Standard Sizes

Standard aggregate sizes shall conform to the requirements prescribed in Table 1 for the size number specified. Conformance shall be determined by means of laboratory sieves having square openings and conforming to Specification E11. Determine the plasticity index by Test Methods D4318.

7 Basis of Classification

Classification of an aggregate is based upon the size number designation and size ranges shown in Table 1. Aggregate shall be sampled in accordance with Practice D75/D75M and tested for grading by Test Method C136/C136M

TABLE 1 Standard Sizes of Processed Aggregate

Size Number	Nominal Size, Square Openings	Amounts Finer Than Each Laboratory Sieve (Square Openings), mass percent														
		100 mm (4 in.)	90 mm (3½ in.)	75 mm (3 in.)	63 mm (2½ in.)	50 mm (2 in.)	37.5 mm (1½ in.)	25.0 mm (1 in.)	19.0 mm (¾ in.)	12.5 mm (½ in.)	9.5 mm (¾ in.)	4.75 mm (No. 4)	2.36 mm (No. 8)	1.18 mm (No. 16)	300 µm (No. 50)	150 µm (No. 100)
1	90 to 37.5 mm (3½ to 1½ in.)	100	90 to 100	...	25 to 60	...	0 to 15	...	0 to 5
2	63 to 37.5 mm (2½ to 1½ in.)	100	90 to 100	35 to 70	0 to 15	...	0 to 5
24	63 to 19.0 mm (2½ to ¾ in.)	100	90 to 100	...	25 to 60	0 to 10	0 to 5
3	50 to 25.0 mm (2 to 1 in.)	100	90 to 100	35 to 70	0 to 15	0 to 5
367	50 to 4.75 mm (2 in. to No. 4)	100	95 to 100	...	35 to 70	10 to 30	0 to 5
4	37.5 to 19.0 mm (1½ to ¾ in.)	100	90 to 100	20 to 55	...	0 to 5
487	37.5 to 4.75 mm (1½ in. to No. 4)	100	95 to 100	10 to 30	0 to 5
5	25.0 to 12.5 mm (1 to ½ in.)	100	90 to 100	0 to 10	0 to 5
56	25.0 to 9.5 mm (1 to ¾ in.)	100	90 to 100	10 to 40	0 to 15	0 to 5
57	25.0 to 4.75 mm (1 in. to No. 4)	100	95 to 100	25 to 60	...	0 to 10	0 to 5
6	19.0 to 9.5 mm (¾ to ¾ in.)	100	20 to 55	0 to 15	0 to 5
67	19.0 to 4.75 mm (¾ in. to No. 4)	100	90 to 100	20 to 55	0 to 10	0 to 5
68	19.0 to 2.36 mm (¾ in. to No. 8)	100	90 to 100	30 to 65	5 to 25	0 to 10	0 to 5
7	12.5 to 4.75 mm (½ in. to No. 4)	40 to 70	0 to 15	0 to 5
78	12.5 to 2.36 mm (½ in. to No. 8)	40 to 75	5 to 25	0 to 10	0 to 5
8	9.5 to 2.36 mm (¾ in. to No. 8)	100	85 to 100	10 to 30	0 to 10	0 to 5
89	9.5 to 1.18 mm (¾ in. to No. 16)	100	90 to 100	20 to 55	5 to 30	0 to 10	0 to 5
9	4.75 to 1.18 mm (No. 4 to No. 16)	100	100	85 to 100	10 to 40	0 to 10	0 to 5
10	4.75 mm (No. 4 to 0 ^A)	100	85 to 100	10 to 40	0 to 10	0 to 5	...	10 to 30

Licensed to TBS PASCHAL LUHEJA
Order # NUMBER/Downloaded: 2026-01-27

^A Screenings.